



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

For new patent application
Inventor: Nasli - Bakir et al
Title: Method for Reducing Emissions and
method for producing a Wooden Product
Filed: 3-24-2004

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03445039.5

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

THIS PAGE BLANK (USPTO)



Anmeldung Nr:
Application no.: 03445039.5
Demande no:

Anmeldetag:
Date of filing: 25.03.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Akzo Nobel N.V.
P.O. Box 9300
6800 SB Arnhem
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se referer à la description.)

Method for reducing emissions and method for producing a wooden product

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

A62D3/00

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT SE SI SK TR LI

THIS PAGE BLANK (USPTO)

METHOD FOR REDUCING EMISSIONS AND METHOD FOR PRODUCING A WOODEN PRODUCT

The present invention relates to a method for reducing emissions from a glued
5 wooden product. It also relates to a method for producing a wooden product, products
obtainable by the methods, and a fluid composition for use in the methods.

Emissions of gaseous substances from wooden products may have different
origin. Solid wood may itself emit substances such as terpenes and aldehydes, usually
referred to as volatile organic compounds (VOC), and some adhesive systems used for
10 joining wood materials may emit various substances from the glue lines. Such emissions
may be, for example, formaldehyde from phenolic- or amino resin based adhesive
systems, and isocyanates from emulsion polymer isocyanate (EPI) adhesive systems.

There is a growing concern about emission of substances in general, and
emission of formaldehyde in particular, from building materials made of glued wood such
15 as laminated beams.

When producing laminated beams, usually, a curable adhesive system is applied
onto wooden lamellae, which are subsequently arranged into an assembly of lamellae.
The assembly is then pressed, usually under heat or high-frequency electromagnetic
fields, and the adhesive system is cured. After pressing the assembly, a planing step is
20 usually performed on the surfaces transversely to the plane of adhesive application in
order to remove excess adhesive and any unevenness resulting from assembling the
individual lamellae. The final laminated beam will have a plurality of glue lines exposed to
open air, as well as newly planed wooden surfaces. It has been found that the exposed
glue lines may emit a significant amount of gaseous substances, such as formaldehyde.
25 Also, the newly planed wooden surfaces may emit gaseous substances, such as
terpenes and aldehydes.

WO 02/072323 A1 and WO 02/072324 A1 disclose methods of reducing
emission of formaldehyde from layered products but do not deal with emissions from an
exposed glue line.

30 It is an object of the present invention to provide a method for reducing
emissions from a glued wooden product, and to provide a method for producing a
wooden product, which has low emissions of gaseous substances. It is a further object of
the present invention to provide products obtainable by the methods and a wooden
product having low emissions of aldehydes or terpenes and, finally, a fluid treating
35 composition for use in the methods.

By wooden materials is herein meant any type of materials originating from wood. This includes both materials of solid wood and, for example, materials made of fibres, particles, and chips of wood.

According to the invention it has surprisingly been found possible to achieve the
5 above mentioned objects by a method for reducing emissions of one or more gaseous substances from an assembly of at least two pieces of wooden materials which have been glued together, comprising planing on at least one of the sides having glue lines exposed, followed by treating the at least one planed sides with one or more treating substances reactive to the one or more gaseous substances. Suitably, the pieces of
10 wooden material are wooden lamellae. Suitably, at least one of the gaseous substances is emitted from an exposed glue line. It is also suitable that at least one of the gaseous substances is emitted from a solid wood surface.

According to the invention it has also surprisingly been found possible to achieve the above mentioned objects by a method for producing a wooden product comprising
15 the steps of: applying an adhesive system onto one or more wooden lamellas, assembling two or more wooden lamellas into an assembly, pressing the assembly, planing at least one of the sides of the assembly having glue lines exposed, and, treating the one or more planed sides by application of one or more treating substances reactive to one or more gaseous substances emitted from the at least one planed side. The
20 wooden product is suitably a laminated wooden product.

"Reactive to one or more gaseous substances" refers to a capability of reducing the total emissions thereof with at least 5%, preferably at least 10%, even more preferably at least 25%, most preferably at least 50%.

The invention is not restricted to the use of any particular type of adhesive
25 system. Suitable adhesive systems to be used in the method of the invention are curable adhesive systems such as amino resin based adhesive systems, phenolic resin based adhesive systems and isocyanate based adhesive systems. Examples of amino resin based adhesive systems are melamine-formaldehyde-, melamine-urea-formaldehyde-, and urea-formaldehyde-based adhesive systems. Examples of phenolic resin based
30 adhesive systems are phenol-formaldehyde-, phenol-resorcinol-formaldehyde and resorcinol-formaldehyde based adhesive systems. Examples of isocyanate based adhesive systems are polyurethane based adhesive systems and emulsion polymer isocyanate (EPI) based adhesive systems. Suitably, the adhesive is cured during, or in connection to, the pressing step. However, also non-curable adhesive systems such as
35 adhesive systems based on vinylester polymers can be used. Examples of vinylester based adhesive systems are polyvinylacetate- ethylene-vinylacetate- and polyvinylpropionate based adhesive systems.

The application of adhesive onto lamellae and assembling of all lamellae are suitably performed in separate steps. Alternatively, it is also suitable that each lamella is applied with the adhesive system at different points of time, the assembly is gradually built-up with the lamellae most recent having been applied with the adhesive system.

5 The planing, according to the methods of the invention, is suitably performed on two sides of the assembly having glue lines exposed.

Suitably, the one or more treating substances are reactive to one or more gaseous substances emitted from the glue line. Also suitable, the one or more treating substances are reactive to one or more gaseous substances emitted from solid wood.

10 The gaseous substances according to the invention may be of different types. One group of substances which may be emitted from a glue line, is aldehydes, such as acetaldehyde, formaldehyde, glutaraldehyde, propionaldehyde, n-butyraldehyde, isobutyraldehyde, hexanal and furfural. Another group of substances which may be emitted from a glue line is isocyanates, such as methyl isocyanate, hexamethylene-1,6-
15 diisocyanate, 4,4-methylenediphenyl isocyanate, toluene 2,4-diisocyanate, and isophorone diisocyanate. Substances which may be emitted from solid wood are, for example, terpenes such as the monoterpenes α - and β -pinene, 3-carene, and limonene, as well as aldehydes such as acetaldehyde, propanal, butanal, pentanal, hexanal and benzaldehyde.

20 In a first aspect of the methods of the present invention, one gaseous substance is suitably an aldehyde, preferably formaldehyde. Then, one or more treating substances are suitably reactive to an aldehyde, preferably formaldehyde. Preferably, the one or more treating substances contain an amino or amide group, of which examples of substances are guanamines, urea, thiourea, biuret, semicarbazides, succinamide,
25 hexamethylenediamine, ethanol amine, ethylene amines, proteins, peptides, hydrazides and ammonium salts such as ammonium carbonate, mono- and diammonium phosphate, ammonium sulphide, and ammonium sulphite. Other sulphites, such as potassium or sodium sulphite can also be used. Also proteins like glutenin, casein, and zein, or protein-containing materials such as flour, whey and protein-containing starch. Hydroxy group
30 containing substances may also be used as treating substances such as alcohols and polyvinylalcohol. Also carbohydrates, such as mono- di- and polysaccharides can be used. Preferably, amino- or amido group containing substances are used. Most preferably, the at least one treating substance is urea or a urea derivative.

35 In a second aspect of the methods according to the invention, one gaseous substance is suitably an isocyanate. Then, one or more treating substances are suitably reactive to an isocyanate. Suitable treating substances include substances containing an amino or amide group, of which examples of substances are guanamines, urea, thiourea,

biuret, semicarbazides, succinamide, hexamethylenediamine, ethanol amine, ethylene amines, proteins, peptides, hydrazides and ammonium salts such as ammonium carbonate, ammonium sulphide, and ammonium sulphite. Hydroxy group containing substances may also be used as treating substances such as alcohols and polyvinylalcohol. Also carbohydrates, such as mono- di- and polysaccharides can be used. A further suitable treating substance is water. Preferably, the at least one treating substance is an amino- or amido group containing substance.

In a further aspect of the methods according to the invention, the gaseous substances suitably belong to the group of terpenes. Then, the one or more treating substances are suitably reactive to terpenes. Suitably, the treating substances belong to the group of unsaturated aldehydes, such as alkenals and alkdienals, or hydroxy group containing substances such as alcohols and polyvinylalcohol. Preferably, the at least one treating substance is an unsaturated aldehyde such as pentenal, hexenal, or octenal.

A treating substance may be used in the methods of the invention as a single component. However, the one or more treating substances are suitably components of a treating composition. The treating composition according to the methods of the invention suitably comprises a solvent for the one or more treating substances. Suitable solvents are water, alcohols such as methanol, ethanol and glycols, and esters such as butyldiglycol acetate. Preferably, water is used as solvent. Mixtures of solvents may also be used. The choice of solvent may in some cases affect the swelling of fibres at a wooden surface. Preferred solvents in these cases include alcohols, glycols, or glycolic acids. The treating composition suitably comprises from about 0.01 to about 99 weight %, preferably from about 1 to about 80 weight %, most preferably from about 10 to about 60 weight % of the one or more treating substances.

The treating composition according to the methods of the invention suitably comprises an agent for improving the film forming properties of the composition when applied onto a surface, preferably a wooden surface. Suitably, the treating composition comprises a polymer as film forming improving agent, suitably in the form of a polymer dispersion. The polymer dispersion is preferably a dispersion of a polyvinylester, such as polyvinylacetate or its derivatives such as polyvinylalcohol, or a polyacrylate dispersion, most preferably a polyvinylalcohol dispersion. The dry content of the film forming improving agent in the treating composition is suitably from about 0.01 to about 50 weight %, preferably from about 0.02 to about 10 weight %, most preferably from about 0.03 to about 2 weight %.

Suitable methods for treating with the one or more treating substances are, for example spraying, roller coating, curtain coating, and coating with an impregnated pad or wetted cloth. Preferably, the treating with the treating substances is made by spraying or

by roller coating. When two sides of the assembly is treated with the one or more treating substances, both sides are suitably treated simultaneously. In this case, suitably, the upper side is treated by spraying and the under side is treated by roller coating. It is also possible to apply the one or more treating substances in the form of strands, which to an extent of more than 50% covers the glue lines, preferably to an extent of more than 80%, most preferably to an extent of substantially 100%.

It is also possible to treat the sides of the assembly not having any glue lines exposed with the one or more treating substances.

The one or more treating substances are suitably applied in an amount to achieve the desired effect, and the amount depends on which treating substance is used. If a treating composition is used, the treating composition is suitably applied in an amount of from about 0.1 to about 100 g/m², preferably from about 1 to about 50 g/m², most preferably from about 5 to about 30 g/m².

Also a drying step can be added after the one or more treating substances have been applied. Suitable drying means are, for example, infra-red radiation, blowing with warm air, and microwave heating.

In a preferred embodiment of the present invention, a laminated beam is manufactured by applying one of a melamine-formaldehyde-, melamine-urea-formaldehyde-, or phenol-resorcinol-formaldehyde- based adhesive system onto a plurality of wooden lamellae. The lamellae are joined into an assembly and pressed at elevated temperature. The resulting beam is subsequently planed on both sides having exposed glue lines in the longitudinal direction, which sides are then treated by application of a fluid treating composition as described above.

The laminated wooden product according to the invention is suitably a laminated beam, in which is also included other laminated structural materials such as laminated veneer lumber.

It has also been found possible to obtain a product having lower emissions of formaldehyde than similar products made by gluing with adhesive systems based on formaldehyde based resins. Therefore, the invention also concerns a product obtainable by the method of the invention as described above.

The product obtainable by the method of the invention suitably has a formaldehyde emission, according to JAS, standard for structural glued timber MAFF, Supplement No 992, of less than about 0.5 mg/l, preferably less than about 0.3 mg/l.

The invention further concerns a laminated wooden product comprising at least two lamellae, which have been joined with an adhesive system based on a formaldehyde based resin. This laminated wooden product has a formaldehyde emission, according to

JAS, standard for structural glued timber MAFF, Supplement No 992, of less than about 0.5 mg/l, preferably less than about 0.3 mg/l.

Furthermore, the invention concerns a laminated wooden product comprising at least two lamellae joined with a glue line, the laminated wooden product comprises a substance, other than water, reactive to aldehydes, isocyanates or terpenes in close proximity of the surface of the side of the product having at least one exposed glue line.

Furthermore, there is a fluid treating composition, for use in the methods of the invention, comprising a polymer dispersion and a substance, other than water, reactive to at least one of a substance belonging to the group of aldehydes, isocyanates, or terpenes, the rest being substantially a solvent, such as water or an alcohol. The treating composition suitably comprises from about 0.01 to about 50 weight %, preferably from about 0.02 to about 10 weight %, most preferably from about 0.03 to about 2 weight %, of a polymer belonging to the group of polyvinylesters, or their derivatives. In one preferred embodiment, the fluid treating composition comprises from about 0.01 to about 100 weight %, preferably from about 1 to about 80 weight %, most preferably from about 10 to about 60 weight %, of urea or a urea derivative. In a second preferred embodiment, the fluid treating composition comprises from about 0.01 to about 100 weight %, preferably from about 1 to about 80 weight %, most preferably from about 10 to about 60 weight %, of a reaction product of an alcohol and ammonia. In a third preferred embodiment, the fluid treating composition comprises from about 0.01 to about 100 weight %, preferably from about 1 to about 80 weight %, most preferably from about 10 to about 60 weight %, of an unsaturated aldehyde.

The invention will now further be described in connection with the following examples which, however, not should be interpreted as limiting the scope of the invention.

Example 1:

A melamine-urea-formaldehyde (MUF) resin and a conventional acidic hardener was tested as well as a low-formaldehyde-emitting adhesive system comprising a melamine-urea-formaldehyde (MUF) resin, a phenol-resorcinol-formaldehyde (PRF) resin and an acid.

For each adhesive system, the emission from glued structures was tested according to JAS MAFF992. Two sets of glued structures were manufactured for each adhesive system. Five lamellae (135 x 15 x 79 mm) of spruce were assembled and glued together with a mixture resin and hardener spread in an amount of 400 g/m². After pressing and conditioning (20°C at 65 % relative humidity), pieces of 75x25x10 mm were cut out. The glued structures were planed on the two sides having exposed glue lines, in

the longitudinal direction. One of the structures for each adhesive system was treated by spraying on both planed sides with an aqueous composition comprising 40 weight % of urea, and 0.07 weight % of polyvinylalcohol, while the other structure was left untreated. The emission of formaldehyde, expressed as mg/l, according to the test method, was

5 determined for all structures and is shown in table 1.

Table 1.

| Adhesive system | Treatment after planing | Formaldehyde emission (mg/l)) |
|--------------------|-------------------------|-------------------------------|
| MUF/ acid hardener | no | 0.47 |
| MUF/ acid hardener | yes | 0.09 |
| MUF/ PRF/ acid | no | 0.24 |
| MUF/ PRF/ acid | yes | 0.02 |

It is concluded that the present invention gives a significant reduction of emission

10 of formaldehyde both for a conventional MUF resin based adhesive system and for a low-emitting MUF/PRF resin based adhesive system.

THIS PAGE BLANK (USPTO)

8
CLAIMS

1. A method for reducing emissions of one or more gaseous substances from an assembly of at least two pieces of wooden materials which have been glued together, comprising planing on at least one of the sides having glue lines exposed, followed by
5 treating the at least one planed sides with one or more treating substances reactive to the one or more gaseous substances.
2. A method for according to claim 1, wherein at least one of the gaseous substances is emitted from an exposed glue line.
3. A method for according to claim 1, wherein at least one of the gaseous
10 substances is emitted from a solid wood surface.
4. A method for producing a laminated wooden product comprising the steps of:
 - (a) - applying an adhesive system onto one or more wooden lamellas,
 - (b) - assembling two or more wooden lamellas into an assembly,
 - 15 (c) - pressing the assembly,
 - (d) - planing at least one of the sides of the assembly having glue lines exposed, and,
 - (f) - treating the one or more planed sides by application of one or more treating substances reactive to one or more gaseous substances emitted from the at
20 least one planed side.
5. A method according to any one of the claims 1-4, wherein one gaseous substance is an aldehyde.
6. A method according to any one of the claims 1-5, wherein one gaseous substance is formaldehyde.
- 25 7. A method according to any one of the claims 5-6, wherein one treating substance is urea or a urea derivative.
8. A method according to any one of the claims 1-4, wherein one gaseous substance is an isocyanate.
9. A method according to claim 8, wherein one treating substance is a reaction
30 product of an alcohol and ammonia.
10. A method according to any one of the claims 1-9, wherein the one or more treating substances are components of a treating composition.
11. A method according to claim 10, wherein the treating composition comprises from about 1 to about 80 weight % of the one or more treating substances.
- 35 12. A method according to any one of the claims 10-11, wherein the treating composition comprises from about 0.02 to about 10 weight % of a polymer.

13. A method according to any one of the claims 10-12, wherein the treating composition comprises a polyvinylalcohol dispersion.

14. A method according to any one of the claims 4-13, wherein the laminated wooden product is a laminated beam.

5 15. A product obtainable by the method according to any one of the claims 4-14.

16. A laminated wooden product comprising at least two lamellae, which have been joined with an adhesive system based on a formaldehyde based resin, having a formaldehyde emission, according to JAS, standard for structural glued timber MAFF, Supplement No 992, of less than about 0.5 mg/l.

10 17. A laminated wooden product comprising at least two lamellae joined with a glue line, the laminated wooden product comprises a substance, other than water, reactive to aldehydes, isocyanates or terpenes in close proximity of the surface of the side of the product having at least one exposed glue line.

15 18. A fluid treating composition for use in the method of any one of the claims 1-14, comprising a polymer dispersion and a substance, other than water, reactive to at least one of a substance belonging to the group of aldehydes, isocyanates, or terpenes.

19. A fluid treating composition according to claim 18, comprising from about 0.03 to about 2 weight % of a polymer belonging to the group of polyvinylesters, or their derivatives, and from about 1 to about 80 weight % of urea or a urea derivative.

20 20. A fluid treating composition according to claim 18, comprising from about 0.03 to about 2 weight % of a polymer belonging to the group of polyvinylesters, or their derivatives, and from about 1 to about 80 weight % of a reaction product of an alcohol and ammonia.

25 21. A fluid treating composition according to claim 18, comprising from about 0.03 to about 2 weight % of a polymer belonging to the group of polyvinylesters, or their derivatives, and from about 1 to about 80 weight % of an unsaturated aldehyde.

10
ABSTRACT

The present invention relates to a method for reducing emissions of one or more gaseous substances from an assembly of at least two pieces of wooden materials, which have
5 been glued together. It also relates to a method for producing a laminated wooden product, and laminated wooden products having low emissions. It also relates to a fluid treating composition, comprising a polymer dispersion and a substance, other than water, reactive to at least one of a substance belonging to the group of aldehydes, isocyanates, or terpenes.

THIS PAGE BLANK (USPTO)